

Antivegetativa Eco



Long life

Good antifouling power

Free of organotin compounds



Code

1010

Description

Long-lasting and effective antifouling free of organo-stannic compounds.

Use

Suitable for all hulls and compatible with all primers, both synthetic and epoxy.

Appearance of the film

Opaque

Color

Red

Component

1

Hardening

Physical by evaporation of solvents

Specific weight

1,570 gr/ml

Volume of solids

45 %

VOC	320 gr/ liter				
Minimum thickness	60 micron				
Estimated yield	7,5 mq / litro per uno spessore di 60 micron secchi				
Flash point	<table> <tr> <td>Componente A</td><td>34°C</td></tr> <tr> <td>Diluyente</td><td>34°C</td></tr> </table>	Componente A	34°C	Diluyente	34°C
Componente A	34°C				
Diluyente	34°C				
Preparation of surfaces	Apply to prime, clean, contaminant-free substrates at least two coats for a total thickness of about 100 - 12				
Preparation of the product	Synthetic thinner: Mix the product before the use and add the thinner <table> <tr> <td>Component A</td><td>100</td></tr> <tr> <td>Thinner</td><td>5 - 10 %</td></tr> </table>	Component A	100	Thinner	5 - 10 %
Component A	100				
Thinner	5 - 10 %				
Environmental conditions	Ambient temperature: da + 5 a 40°C Temperature of the support: > di 10°C Humidity: 0 - 85 % Ambient temperature: da + 5 a 40°C Temperature of the support: > di 10°C Humidity: 0 - 85 % To prevent the formation of condensation, the temperature of the substrate must be at least 3°C above the dew point.				
Drying and hardening time	For thicknesses of 60 microns: 10°C: 6 hours touch, 12 hours deep 20°C: 6 hours touch, 6 hours deep 30°C: 2 hours touch, 4 hours deep				
Time of overpainting	Minimum: 10°C - 12 hours; 20°C - 6 hours; 30°C - 4 hours Maximum (months): unlimited				

Application

Brush, roller, spray
For brush applications use nylon or pure bristle brushes.
For roller applications use medium-haired rollers.
For application use the cross-coat method.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Lt. 2,500, Lt. 0,750 Diluente 5, 25, 180 lt

