resina color
made in italy
painting the difference

Scheda Tecnica

CEMENTIK

Matt primer

Good adhesion and sanding

Code	0402
Description	Primer filler based on modified glycerophthalic resins
Use	This product is used as a primer coat on wood before applying synthetic enamels or as an intermediate paint on primed metal surfaces.
Appearance of the film	Matt
Color	White
Component	1
Hardening	Physical hardening through evaporation of solvents and oxidative polymerization.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	1,580 gr / ml
Volume of solids	58%
VOC	380 gr/ liter
Minimum thickness	50 – 60 micron
Estimated yield	9 m² / litre for a thickness of 50 microns.
Flash point	Component A 40° C Thinner 34° C
Temperature resistance	80° C continuously, 120° C discontinuously
Preparation of surfaces	New wood: Sand to remove dirt and various contaminants. Old paints: Sanding or washing to remove greases or dirt
Preparation of the product	Mix the product before the use and add the thinner: Component A 100 Thinner Synthetic thinner 5 - 10 % depending on the thickness of the dry film
Environmental conditions	Temperatura da: + 5 a 40°C Temperatura supporto: > di 10°C Umidità: 0 – 80% Per prevenire la formazione di condensa è necessario che la temperatura del supporto sia almeno di 3°C superiore al punto di rugiada.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Tempi di indurimento	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 80 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.
Drying and hardening time	Minimum (hours): 10°C - 12 hours; 20°C - 8 hours; 30°C - 6 hours Maximum: unlimited in the absence of contaminants
Application	Brush or spray
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Comp A: Lt. 2,5 Lt. 0,500

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it