
Scheda Tecnica

DELUX CASA EXTRA





- Water-based acrylic finish
- Highly washable
- Resistant to bad weather

Code	0805
Description	DELUX CASA EXTRA is based on high concentration acrylic resins. Its film has a semi-matt and soft look, which reflect the light uniformely so to give brightness to the place. Fast drying, rsistant to cleaning, anti mold. Thanks to its features it is suitable for all types of wall inside and outside.
Use	The product can be applied on suitably prepared concrete wall surfaces, where a good aesthetic appearance, as well as excellent resistance to washing with detergents, is required.
Film appearance	Matt
Colour	White and colour chart
Hardening	Physical by evaporation of water and coalescence of the polymer
Specific Weight	From 1,480 gr/m

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Solids volume	43 %
VOC	40 gr/ L
Minimum thickness	50 -60 microns
Yield	8,6 mq / L for a thickness of 50 microns dry.
Fire point	Component A > 114°C
Temperature resistance	Max 60°C
Washability	> 15000 hits
Preparation of the surfaces	New surfaces: Prime with acrylic insulation. In case of surfaces with high alkalinity (lime or new ready-mixed plasters) use a universal neutralizing insulator, based on alkali resistant resins. The same treatment is advisable in case of surfaces previously treated with lime or chalking.
Preparation of the product	Mix the product before use and add water Component A 100 Water max 40%
Environmental conditions	Ambient temperature: from + 5 to 40°C Temperature of the surface: > 10°C Humidity: 0 – 85 % To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening

For thicknesses of 50 microns	10°C	20°C	30°C	
Dry to touch	3	1	0,5	hrs
Dry in depth	8	4 -5	2	

Overpainting

Minimum (hrs)	10°C	20°C	30°C
	8	4	3

Application

Brush, roller spray
For brush applications use nylon or pure bristle brushes.
For roller applications use medium bristle rollers.
For its application use the method of the crossed hands.

Shelf life

2 years in a cool and dry place (max. 40ºC)

Packaging

Comp A Lt. 14 Lt. 5 Lt. 2,5

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it