Scheda Tecnica

FINISCH PAV





- Unsaponifiable and resistant to the weather
- It is suitable for any supports
- It is resistant to the abrasion

Code	857
Description	Solvent - based paint made of modified vinyl acrylic resins, with high resistance to the atmospheric agents, alkali and with a good permeability to water vapour.
Use	This product is applied on different substrates such as: plaster, lime plaster, bituminous surfaces, fibre cement.
Appearance of the film	Semi - glossy
Color	White, red and color chart
Component	1
Hardening	Physical hardening through evaporation of solvents
Specific weight	1,3 – 1,4 gr/ml
Volume of solids	45 %

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

VOC	480 gr/ liter
Minimum thickness	60 -80 micron
Estimated yield	7,5 m² / litre for a thickness of 60 microns
Flash point	Component A 34°C Thinner 34°C
Temperature resistance	Max 110° C continually 200° C discontinuously
Preparation of surfaces	New metal supports: Remove dust and contaminants, such as greases and oils, from the surfaces. For new concrete Adequate dust removal: application of a diluted coat, followed after 24 hours by an other coat as it is
Preparation of the product	Mix the product before the use and add the thinner Component A 100 Thinner max 20 % - 30 % (First coat)
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 85 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point

Drying and hardening time

For the thickness of 60 microns	10° C	20° C	30° C
Dry to touch	6	3	2 hours
Dry in depth	48	24	10 hours

Time of overpainting

Minimum (hours)	10° C	20° C	30° C
	24	12	6 hours

Maximum unlimited in the absence of contaminants

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Application	Brush, roller, spray If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium - haired rollers. For the application, it is necessary to use the method of crossing coats
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Comp A Lt. 16 Lt. 4 Thinner 5, 25, 180 lt



Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it