Scheda Tecnica

GRAFFIATO





- Thick coating
- Permeable to water vapour
- Weather - proof

Code	0901
Description	Plastic coating based on acrylic resins and siliceous aggregates, with excellent masking power of the substrate imperfections.
Use	This product can be applied on old and new plasters based on hydraulic binders, on concrete, on old organic and mineral paints, provided they are absorbent and united.
Appearance of the film	Matt
Color	White or color chart
Component	1
Hardening	Physical hardening through evaporation of water and union of the polymer
Specific weight	Da 1,95 gr/ml
VOC	5 gr/ liter

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Estimated yield	1,5 – 2,5 kg / mq
Flash point	Component A > 114°C
Preparation of surfaces	New surfaces: Dry and mature. Remove any efflorescence by brushing or washing. Old surfaces: Remove dust and old paints that are peeling off, widen any cracks and fill them with a filler. Completely eliminate old lime or tempera paints. In the presence of molds, provide for an appropriate anti - mold treatment. Prime surfaces with a fixative such as « SOTTOFONDO ».
Preparation of the product	Mix the product before the use. Component A 100
Environmental conditions	Ambient temperature: from + 8 to 40° C Temperature of the support: > 5° C Humidity: 0 - 75 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.
Precautions:	Do not apply in the presence of surface condensation or under direct sunlight. The humidity of the substrate must be less than 10 %. Protect from the rain for at least 48 hours.
Drying and hardening times	At 25° C for 1 - 2 hours depending on the thickness applied.
Overpainting	After 5 - 6 hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Application	Spatula
Shelf life	1 year in a cool and dry place (max 40° C)
Packs	Comp A Kg. 24

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it