

# IDROLUX EXTRA



Water – dilutable and water – repellent paint

Good breathability

Paint used for the exteriors and the interiors



## Code

0809

## Description

It is a breathable and water – repellent paint used for the exteriors and the interiors. Thanks to their insolubility in water, the special pigments that compose it give the product great breathability and water repellency with a long duration in time. Outside the product consumes oneself evenly in time and there aren't peelings and swellings. « IDROLUX EXTRA » has excellent features in application.

## Use

It can be applied on old and new plasters, concrete surfaces, gypsum and plasterboard, old paints, and so on. « IDROLUX EXTRA » has a good high flexibility in application, coverage and resistance to the dry abrasion.

## Appearance of the film

matt

## Colour

White – color chart

## Component

1

## Hardening

Evaporation of the solvents and union of the polymer

### Specific weight

From 1,620 gr/ml

### VOC

30 gr/ liter

### Estimated yield

8 - 9 m<sup>2</sup> / litre for the smooth supports with medium absorption

### Flash point

Component A > 114° C

### Preparation of surfaces

**New surfaces:**  
Make sure that the supports are completely dry. If there are molds, treat the surface with suitable products.  
Remove possible efflorescence and paints that are peeling off with brushes and washes.  
Prime the surface with an acrylic fixative product.

**Old surfaces:**  
Remove old paints that are peeling off. Tempera and lime paintings must be removed with brushes and washes.

### Preparation of the product

Mix the product before the use and add water  
Component A 100  
Water 1° coat 20 - 25 %  
2° coat 10 - 15 %

### Environmental conditions

Ambient temperature: from + 8 to 40° C  
Temperature of the support: > di 10° C  
Humidity: 0 - 80 %  
In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.

### Drying and hardening time

| For the thickness of 50 microns | 10° C | 20° C | 30° C     |
|---------------------------------|-------|-------|-----------|
| Dry to touch                    | 3     | 1     | 0,5 hours |
| Dry in depth                    | 8     | 4 -5  | 2 hours   |

### Time of overpainting

| Minimum (hours) | 10° C                                    | 20° C | 30° C |
|-----------------|------------------------------------------|-------|-------|
|                 | 8                                        | 4     | 3     |
| Maximum         | unlimited in the absence of contaminants |       |       |

### Application

Brush, roller  
If you use the brush, you have to use nylon or natural bristle brushes.  
If you use the roller, you have to use medium-haired rollers.  
For the application, it is necessary to use the method of crossing coats.

### Shelf life

2 years in a cool and dry place (max 40° C)

### Packs

Comp A Lt. 14 Lt. 5 Lt. 2,5

