Scheda Tecnica

# LUXURY






- Glossy textured finish based on water
- High washability
- It is suitable for internal and external spaces

| | |
|---|---|
| Code | 0905 |
| Description | Paint based on vynilversatic copolymers in aqueous dispersion. It is suitable for the rooms of hospitals, schools, and for all environments where a high standard of cleanliness is required. |
| Use | This product can be applied to old and new plasters based on hydraulic binders, concrete, plaster and plasterboard surfaces. It is also used on old organic or inorganic paints, provided they are well adherent.<br>Avoid the application on wet or alkaline substrates. |
| Appearance of the film | Glossy |
| Color | White and color chart |
| Component | 1 |
| Hardening | Physical hardening through evaporation of water and union of the polymer |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

| | |
|---|---|
| Specific weight | Da 1,170 gr/m |
| Volume of solids | 43 % |
| VOC | 71,53 gr/ liter |
| Minimum thickness | 100 micron |
| Estimated yield | 4,3 m² / litre for a thickness of 100 microns |
| Flash point | Component A > 114°C |
| Preparation of surfaces | New surfaces:<br>Prime with an acrylic insulating product; in the presence of surfaces with high alkalinity (lime plasters), use a universal neutralizing insulating product, based on resistant alkali resins.<br>In the presence of lime or tempera paints, remove them entirely from the surface by washing or by the abrasion.<br>In the presence of mold, provide an adequate anti - mold treatment with suitable products. |
| Preparation of the product | Mix the product before the use<br>Component A 100<br>Water max 5 % to reduce the textured effect |
| Environmental conditions | Ambient temperature: from + 5 to 40° C<br>Temperature of the support: > 10° C<br>Humidity: 0 - 75 %<br>In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

| | |
|---|---|
| Drying and hardening time | At 25° C and 65 % of humidity 1 - 2 hours |
| Time of overpainting | 6 hours |
| Application | Roller, brush only for small touches.<br>For the roller application, use medium - grained sponge rollers. |
| Shelf life | 2 years in a cool and dry place (max 40° C) |
| Packs | Comp A Lt. 14; Lt. 5; Lt. 2,5. |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it