

Scheda Tecnica

Micos







One - coat synthetic finish

It has a good anti - corrosive protection



Description

Hand - finish based on modified glycerophthalic resins. It has a dual anti – corrosive chemical action and with a barrier effect.

Use

This product is used as a one - coat finish directly on clean sheet metal for the protection of wood and metal works where you want to give an antiqued effect.

Appearance of the film

Color

Color chart

Component

1

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Scheda Tecnica

Hardening Physical hardening through evaporation of solvents and oxidative polymerization Specific weight 1,620 Volume of solids 50% 400 gr/liter Voc Minimum thickness 80 - 100 micron Estimated yield 6,250 m² / litre for a thickness of 80 microns Flash point 27°C 80° C continuously, 120° C discontinuously. Temperature resistance Preparation of surfaces New steel: Brushing, greasing, anyway clean surfaces. Old paints: Brushing, dust removal



Scheda Tecnica

Preparation of the product

Mix the product before the use and add the thinner

Component A 100

Thinner 10 - 20 % depending on the thickness of the dry film to be

applied.

Environmental conditions

Ambient temperature: from + 5 to 40° C

Temperature of the support: $> 10^{\circ}$ C Humidity: 0 - 85%

In order to prevent the formation of condensation, it is necessary that the

temperature of the substrate is at least 3° C above the dew point.

Drying and hardening time

For the thickness of 80 microns 10° C 20° C 30° C Dry to touch 8 3 1 hours

Dry in depth 24 12 5 hours

Time of overpainting

Minimum (hours) 10° C 20° C 30° C 24 12 6 hours

Maximum unlimited in the absence of contaminants

Application Brush, roller, spray

If you use the brush, you have to use nylon or natural bristle brushes.

If you use the roller, you have to use medium - haired rollers.

For the application, it is necessary to use the method of crossing coats.

Shelf life 2 years in a cool and dry place (max 40° C)

Packs Comp A Lt. 2,5 - Lt. 0,750 Thinner Lt. 25 - Lt. 5 - Lt. 1