

Scheda Tecnica

NUBILAC SATINATO









High coverage

Excellent washability

Quick drying



Code

0309

Description

Satin enamel based on acrylic resins in aqueous emulsion and precious pigments, which give the product a very high coverage, high yield, exceptional washability, high resistance to chemical and atmospheric agents, and perfect adhesion on various types of support such as PVC, light alloys and old paintwork. Being completely solvent-free, the new NUBILAC is non-toxic, odorless and non-flammable and can also be applied in closed or poorly ventilated environments without any danger as it does not create harmful or disturbing vapors.

Use

The product can be applied on various types of surfaces such as PVC, light alloys, old paints, wood, iron, glass, wall and concrete surfaces, on the condition that they are properly prepared and primed.

Appearance of the film

satin

Colour

White - Black - Colour chart

Component

1



Scheda Tecnica

Physical by evaporation of water and coalescence of the polymer. Hardening Specific weight From 1,30 gr/lt 38,8 % Volume of solids VOC 48 gr/liter 50 -60 micron Minimum thickness Estimated yield 6,4 m² /L for a thickness of 50 microns dry Flash point Component A > 114°C Max 60°C Temperature resistance New surfaces: Prime with acrylic insulation IMPRIMITURA ACRILICA. In case of Preparation of surfaces surfaces with high alkalinity (lime plasters) use the universal neutralizing insulator H95 IMPRIMITURA based on resistant alkali resins. The same treatment is advisable in case of surfaces previously treated with lime or chalking. Metal surfaces: prime with the water-based anti-rust product UNDER. Preparation of the product Mix the product before use and add water. Component A 100 10-15% max. Water **Environmental conditions** Ambient temperature: from + 5 to 40°C Temperature of the surface: > 10°C 0 - 85 % Humidity:

must be at least 3°C higher than the dew point.

To prevent the formation of condensation the temperature of the surface



Scheda Tecnica

Drying and hardening	For thicknesses of 50 microns	10°C	20°C	30°C
	Dry to touch	3	1	0,5

Dry in depth 8 4 -5 2

hrs

Time of overpanting

Minimum (hrs) 10°C 20°C 30°C 8 4 3

Maximum Unlimited, except for the presence of contaminants on the

surface

Application

Brush, roller spray

For brush applications use nylon or pure bristle brushes.

For roller applications use medium pile rollers.

For the application use the method of the crossed hands.

Shelf life

2 years in a cool and dry place (max 40°C)

Packs

Comp A Lt. 2,5 Lt. 0,750