Scheda Tecnica

# PITTURA PER PISTE CICLABILI ALL'ACQUA





- Waterproof barrier
- Highly walkable and resistant to abrasion
- Resistant to water stagnation

| | |
|---|---|
| Code | 875 |
| Description | Elastic finish based on acrylic styrene emulsions and special internal additives that give the product excellent water repellency, high resistance to UV rays and to alkaline environments. |
| Use | Suitable for painting asphalt cycle paths or athletic tracks. After drying, the product forms an elastic layer resistant to weathering and abrasion. |
| Appearance of the film | matt |
| Colour | White – Colour chart |
| Component | 1 |
| Hardening | Physical by evaporation of water and coalescence of the polymer. |
| Specific weight | From 1,320 – 1,380 gr/ml |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

| | |
|---|---|
| Volume of solids | 58 % |
| VOC | 120 gr/ liter |
| Minimum thickness | 500 micron |
| Estimated yield | 1,1 m² /L for a thickness of 500 microns dry. |
| Flash point | Component A > 114°C |
| Elongation % | 50% for a dry thickness of 2000 microns. |
| Preparation of surfaces | Do a thorough cleaning by removing dust, peeling parts, grease and other contaminants. On surfaces with presence of old paints, prime with a hand diluted with 40-50% of the product. On new surfaces prime with a hand diluted 50%. Then, apply a second coat diluted 5-10%.<br>The surface must be dry, since the presence of excessive humidity inside the surface, in the phase of solar radiation, can generate steam which causes the formation of bubbles and the subsequent detachment of the coating. |
| Preparation of the product | Mix the product before use.<br>For trowel applications the product must not be diluted.<br>For roller applications dilute the product with max. 5% of water |
| Environmental conditions | Ambient temperature: from + 5 to 40°C<br>Temperature of the surface: > 10°C<br>Humidity: 0 – 85 %<br>To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point<br>. |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

## Drying and hardening

| For thicknesses of 500 microns | 10°C | 20°C | 30°C | |
|---|---|---|---|---|
| Dry to touch | 24 | 6 | 1 | hrs |
| Dry in depth | 24 | 8 | 2 | |

## Time of overpainting

| Minimum (hrs) | 10°C | 20°C | 30°C |
|---|---|---|---|
| | 24 | 8 | 3 |

Maximum Unlimited, except for the presence of contaminants on the surface

## Application

Spatula, roller.
For roller applications, use medium pile or honeycombed rollers

## Shelf life

1 year in a cool and dry place (max 40°C)

## Packs

Comp A Lt. 14

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it