

## Scheda Tecnica

## **PITTURE PER BAGNI E CUCINE**



Water-soluble anti-mould paint

Breathable paint

Suitable for indoor use



Code 0804

Description Vinylversatic resin-based water paint,breathable,anti-mold.

Use It can be applied to old and new plaster, concrete, gypsum and plasterboard, old paint, etc.

Appearance of the film Matt

Color White and colour chart

Component 1

Hardening Physical by evaporation of water and coalescence of the polymer.

Specific weight From 1,690 gr/ml

VOC 30 gr/ liter

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



## **Scheda Tecnica**

Estimated yield

8 - 9 mg / I for smooth medium absorption surfaces

Flash point

Component A

> 114°C

Preparation of surfaces

Make sure the substrates are well dried, if mold is present, treat the surface as follows: clean the surface with our product SD SPRAY ANTIMUFFA. Wipe dry with a damp cloth. After that, apply an even coat of SANIMUFF facade reclaiming solution and let it act for 24 to 48 hours. Then apply two coats of Bathroom and Kitchen Paint

Remove any efflorescence and detaching paint by brushing and washing.

Prime with acrylic fixative.

Old Paints:

Remove old, detaching paints; tempera and lime-based paints should be removed by brushing and washing.

Preparation of the product

 $\begin{array}{ccc} \text{Mix the product before use and add water} \\ \text{Component A} & 100 \\ \text{Water} & \text{max} & 30\% \\ \end{array}$ 

**Environmental conditions** 

Ambient temperature: da + 5 a  $40^{\circ}$ C Temperature of the surface: > di  $10^{\circ}$ C Humidity: 0 -  $80^{\circ}$ M

To prevent the formation of condensation, the temperature of the surface must be

at least 3 ° C higher than the dew point.

Drying and hardening time

For thicknesses of 50 microns  $10^{\circ}\text{C}$   $20^{\circ}\text{C}$   $30^{\circ}\text{C}$  Dry to the touch 3 1 0,5 ore Dry in depth 8 4-5 2

Time of overpainting

Minimum: (hrs) 10°C 20°C 30°C 8 4 3

Maximum: unlimited, except for the presence of contaminants on the surface



## Scheda Tecnica

Application Brush and paint roller.

For brush applications use nylon or pure bristle brushes.

For roller applications use medium-hair rollers.

For the application use the method of the crossed hands

Shelf life 2 years in a cool and dry place (max 40 ° C)

Packs Comp A Lt. 14 Lt. 5 Lt. 2,5

