

QUARZO BUCCIA D'ARANCIA



Thick coating

Permeable to water vapour

Resistant to the bad weather



Prodotti Professionali

Code

0906

Description

Based on water dispersion copolymers, opaque pigments and selected quartzes, the product is a quartz plastic coating with an orange peel final effect with remarkable characteristics of resistance to the impacts, abrasions and washings.

Use

This product can be applied on old and new plasters based on hydraulic binders, on concrete, on old organic and mineral paints, provided they are absorbent and united.

Appearance of the film

Matt

Color

White or color chart

Component

1

Hardening

Physical hardening through evaporation of water and union of the polymer

Specific weight

From 1,670 gr/ml

VOC

15 gr/ liter

Estimated yield

1 - 1,5 kg / m²

Flash point

Component A > 114°C

Preparation of surfaces

New surfaces:
Dry and mature. Remove any efflorescence by brushing or washing.
Old surfaces:
Remove dust and all old paints that are peeling off, widen any cracks and fill them with a filler. Completely eliminate old lime or tempera paints.
In the presence of molds, provide for an appropriate anti - mold treatment.
Prime surfaces with an acrylic fixative such as « IMPRIMITURA ACRILICA » or « SOTTOFONDO ».

Preparation of the product

Mix the product before the use.
Component A 100
Thinner Water
Brush 1° coat dilute to 25 - 30 %; 2° coat to 10 - 15 %
Roller: 10 - 15 % max.

Environmental conditions

Ambient temperature: from + 8 to 40° C
Temperature of the support: > 5° C
Humidity: 0 - 75 %
In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.

Precautions:

Do not apply in the presence of surface condensation or under direct sunlight.
The humidity of the substrate must be less than 10 %.
Protect from the rain for at least 48 hours.

Drying and hardening time

At 25° C for 0,5 - 1 hour depending on the thickness applied

Time for overpainting

After 4 - 5 hours

Application

« QUARZO BUCCIA D'ARANCIA » is applied with a brush or a wool roller. In addition, it is worked with an orange peel roller and it is diluted with max 3 - 4 % of water; so we obtain the classic orange peel effect.

Shelf life

1 year in a cool and dry place (max 40° C)

Packs

Comp A Lt. 14, Lt. 4, Lt. 2,5

