Scheda Tecnica

# R 25 PRIMER W





- Pigmented water-soluble acrylic sealer
- Sealer for pedestrian and mural surfaces
- For waterproofing and painting cycles

| | |
|---|---|
| Code | 0644 |
| Description | Pigmented water-based sealer based on acrylic resins in aqueous solution with a high degree of unsaponibility. R 25 is a product ready to use, but, if necessary, it can be diluted with water. |
| Use | The product is used as a support for anchoring successive layers of liquid waterproofing such as RESIN GUAINA or ECOMIRROR TETTI, and as sealer after having done a coat of MATT VETRO. Also suitable for various types of conglomerates, provided that they are absorbent. |
| Appearance of the film | Translucent |
| Colour | Red oxide |
| Component | 1 |
| Hardening | Physical by evaporation and coalescence of the polymer |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

| | |
|---|---|
| Specific weight | 1,01 gr/ml |
| Volume of solids | 26 % |
| VOC | 5 gr/ liter |
| Minimum thickness | 5 – 10 micron |
| Estimated yield | 26 mq /L for a thickness of 10 microns dry |
| Preparation of surfaces | Make sure that the surface is dry, remove any efflorescence. Eliminate old paints with a brush. Remove completely old layers of lime paints or tempera.<br>Level any irregularities, plug holes, sand. |
| Preparation of the product | Component A 100<br>Product ready to use. If necessary, dilute with water according to the absorption of the surface |
| Environmental conditions | Ambient temperature: from + 5 to 40°C<br>Temperature of the surface: > 5°C<br>Humidity: 0 – 75 %<br>Avoid applications when there is condensation on the surface or under the direct action of the sun. |
| Drying and hardening times | A 25°C e 65% UR<br>Dry to touch 35 – 45 minutes |
| Time for overpainting | 4 – 5 hours |
| Application | Brush and paint roller.<br>For brush applications use nylon or pure bristle brushes<br>For roller applications use medium pile rollers.<br>For the application use the method of the crossed hands |
| Shelf life | 2 years in a cool and dry place (max 40°C) |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

| | |
|---|---|
| Confezioni | Comp A Lt. 15. |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it