

Sea Paint



Long lasting

Good anti - fouling power

Free from organostannic compounds



Code

1003

Description

Anti - fouling product with long lasting and efficacy; it is free from organostannic compounds.

Use

This product is used for all hulls and it is compatible with all synthetic and epoxy substrates..

Appearance of the film

Matt

Color

Red, black, blue, white

Component

1

Hardening

Physical hardening through evaporation of solvents

Specific weight

1,570 gr/lt

Volume of solids	45%			
VOC	320 gr/lt			
Minimum thickness	60 micron			
Estimated yield	7,5 m ² / litre for a thickness of 60 microns			
Flash point	Component A	34° C		
	Thinner	34° C		
Preparation of surfaces	On substrates primed, clean and free of contaminants, apply two coats for a total thickness of about 100 - 120 microns.			
Preparation of the product	Mix the product before the use and add the thinner			
	Component A	100		
	Thinner	5 - 10 %		
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 85 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.			
Drying and hardening time	For the thickness of 60 microns	10° C	20° C	30° C
	Dry to touch	6	3	2 hours
	Dry in depth	12	6	4 hours
Time of overpainting	Minimum (hours)	10° C	20° C	30° C
		12	6	4 hours
	Maximum	unlimited in the absence of contaminants		

Application

Brush, roller, spray

If you use the brush, you have to use nylon or natural bristle brushes.

If you use the roller, you have to use medium - haired rollers.

For the application, it is necessary to use the method of crossing coats.

Shelf life

2 years in a cool and dry place (max 40° C

Packs

Comp A	0,750 Lt. - 2,5 Lt.	Thinner	5 Lt. - 25 Lt.
--------	---------------------	---------	----------------

