Scheda Tecnica

# TENNIS






- Excellent adhesion on cement and old paints
- Good resistance to alkaline and acid solutions
- Excellent UV resistance

| | |
|---|---|
| Code | 1001 |
| Description | Solvent-based modified chlorine vinyl resin based paint with good penetrating power |
| Use | For the protection of concrete tennis courts |
| Appearance of the film | matt |
| Colour | Red |
| Component | 1 |
| Hardening | Physical by evaporation if solvents |
| Specific weight | 1,350 gr/ml |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

| | |
|---|---|
| Volume of solids | 38 % |
| VOC | 600 gr/ liter |
| Estimated yield | 5 -6 m² / L per layer and on smooth and medium absorption surfaces |
| Flash point | Component A 34°C<br>Thinner 34°C |
| Preparation of surfaces | New surfaces:<br><br>Make sure that the surface is free from humidity, remove any efflorescence by brushing.<br>Old surfaces: Remove any peeling parts, level out any irregularities, seal any cracks.<br>Old paints: Remove by brushing peeling paints and other contaminants. In case of mould, do a preventive wash with a suitable restorer before brushing. |
| Preparation of the product | Mix the product before use and add the thinner<br><br>Component A 100<br>Thinner max 10% - 15% synthetic thinner |
| Environmental conditions | Ambient temperature: from+ 5 to 40°C<br>Temperature of the surface: >10°C<br>Humidity: 0 – 80 %<br>Humidity of the surface < 10%<br>To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point |
| Drying and hardening times | 10°C 20°C 30°C<br>Dry to touch 6 3 2 hours<br>Dry in depth 12 6 4 |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

| | |
|---|---|
| Time for overpainting | Minimum (hours) 10°C 20°C 30°C<br>12 6 4<br>Maximum Unlimited, except for the presence of contaminants on the surface |
| Application | Brush, roller, spray<br><br>For brush applications use nylon or pure bristle brushes.<br>For roller applications use medium pile rollers.<br>For the application use the method of the crossed hands |
| Shelf life | 2 years in a cool and dry place (max 40°C) |
| Packs | Comp A kg Thinner 5, 25, 180 lt |

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it