

Scheda Tecnica

Toplacaucciù









Excellent adhesion on cement and old paints

Resistant to continuous immersion in water

Excellent UV resistance



Code

Description

Solvent-based modified vinyl-acrylic resin-based paint with good penetrating power

Use

For the protection of new and painted concrete swimming pools

Appearance of the film

Colour

Light blue

Component

1

Hardening

Physical by evaporation of solvents

Specific weight

1,400

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Scheda Tecnica

Volume of solids

600 gr/lt

38%

Estimated yield

5 -6 m²/L per layer and on smooth and medium absorption surfaces.

Flash point

Voc

34°C

Preparation of surfaces

New surfaces:

Make sure that the surface is free from humidity, remove any efflorescence by brushing.

Old surfaces:

Remove any peeling parts, level out any irregularities, seal any cracks.

Old paintings:

Remove by brushing peeling paints and other contaminants. In case of mould, do a

preventive wash with a suitable restorer before brushing.

Wait at least 4 days from the application of the product to fill the tub or swimming pool with water.

Preparation of the product

Mix the product before use and add the thinner.

Component A 100

Thinner max 20% -25% synthetic thinner

Environmental conditions

Ambient temperature: from + 5 to 40°C

Temperature of the surface: $> di 10^{\circ}C$ Humidity: 0 - 80 %Humidity of the surface < 10%

To prevent the formation of condensation the temperature of the surface

must be at least 3°C higher than the dew point.

Drying and hardening times

	10°C	20°C	30°C	
Dry to touch	6	3	2 hrs	
Dry in depth	12	6	4	



Scheda Tecnica

Time for overpainting Minimum (hrs) 10°C 20°C 30°C 12 4 Maximum Unlimited, except for the presence of contaminants on the surface **Application** Brush, roller spray For brush applications use nylon or pure bristle brushes. For roller applications use medium pile rollers. For the application use the method of the crossed hands 2 years in a cool and dry place (max 40°C) Shelf life **Packs** Lt. 0,750 - Lt. 4 - Lt. 16