

## Scheda Tecnica

## **VERO LEGNO ECO**









Water - based wood filler

Waxed effect, fungicide

Weather - resistant



Code

0307

Description

Fungicidal filler based on acrylic resins in water emulsion with wax effect for wood

Use

Fungicidal primer with wax effect, a wood protection based on acrylic resins in water emulsion and anti - mould additives, non - toxic to humans. In addition, « Vero Legno Eco » fills the porosity of the wood and protects it. It is suitable for new, old and painted wood.

Aspect of the film

Matt

Colour

Colourless

Components

1

Hardening

Evaporation and union of the polymer

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



## Scheda Tecnica

Specific weight 1,000 – 1,030 gr / ml

Volume of solids 25 %

VOC 40 gr/ litre

Estimated yield 6 - 7 m<sup>2</sup> / litre for woods with medium absorption

Flash point ND

Preparation of surfaces New or restored surfaces:

Sand in order to remove raised wood fibers, any traces of resin should be removed

using a nitro thinner. Fill any imperfections, sand and remove dust.

Give a first coat of filler diluted in 10 - 20 % water.

After drying, sand and apply a second coat for indoor applications, 3 coats for

outdoor applications.
Already painted surfaces:

Remove old layers of paints that are peeling off and roughen the surface.

Sand any fillings and remove dust. Apply the primer as indicated above.

Preparation of the product Mix the product

Mix the product before the use and add water

Component A 100

Thinner Water 10 - 20 % first coat

Second coat as it is

**Environmental conditions** 

Ambient temperature: from + 8 to 35° C

Temperature of the substrate:  $> 5^{\circ}$  C Humidity: 0 - 75%



## Scheda Tecnica

Drying and hardening time

At 20° C and 65 % UR

Dry to touch 1 hour; overpaintable after 7 hours

**Application** 

Brush, roller, spray

For brush application, use nylon or natural bristle brushes.

For roller application, use medium - haired rollers. For application, use the method of crossing coats.

Shelf life

2 years in a cool and dry place (max 40° C)

**Packs** 

Comp A Lt. 2,5 Lt. 0,750