Scheda Tecnica

VERO LEGNO ECO





Water - based wood filler

Waxed effect, fungicide

Weather - resistant

Code	0307
Description	Fungicidal filler based on acrylic resins in water emulsion with wax effect for wood
Use	Fungicidal primer with wax effect, a wood protection based on acrylic resins in water emulsion and anti - mould additives, non - toxic to humans. In addition, « Vero Legno Eco » fills the porosity of the wood and protects it. It is suitable for new, old and painted wood.
Aspect of the film	Matt
Colour	Colourless
Components	1
Hardening	Evaporation and union of the polymer

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	1,000 – 1,030 gr / ml
Volume of solids	25 %
VOC	40 gr/ litre
Estimated yield	6 - 7 m² / litre for woods with medium absorption
Flash point	ND
Preparation of surfaces	New or restored surfaces: Sand in order to remove raised wood fibers, any traces of resin should be removed using a nitro thinner. Fill any imperfections, sand and remove dust. Give a first coat of filler diluted in 10 - 20 % water. After drying, sand and apply a second coat for indoor applications, 3 coats for outdoor applications. Already painted surfaces: Remove old layers of paints that are peeling off and roughen the surface. Sand any fillings and remove dust. Apply the primer as indicated above.
Preparation of the product	Mix the product before the use and add water Component A 100 Thinner Water 10 - 20 % first coat Second coat as it is
Environmental conditions	Ambient temperature: from + 8 to 35° C Temperature of the substrate: > 5° C Humidity: 0 - 75 %

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening time	At 20° C and 65 % UR Dry to touch 1 hour; overpaintable after 7 hours
Application	Brush, roller, spray For brush application, use nylon or natural bristle brushes. For roller application, use medium - haired rollers. For application, use the method of crossing coats.
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Comp A Lt. 2,5 Lt. 0,750



Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it