Scheda Tecnica

BIANCO TIX





- Water - dilutable paint
- Excellent coverage
- Breathable for internal spaces

Code	0814
Description	Paint in emulsion based on vynilversatic resin in water dispersion.
Use	This product is indicated for the painting of interior wall surfaces; it has a good covering power and it is breathable. It is easy to apply for its anti - drip power.
Appearance of the film	Matt
Color	White
Component	1
Hardening	Physical hardening through evaporation of water and union of the polymer
Peso specifico	Da 1,700 gr/ml
VOC	15 gr/ liter

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Estimated yield	8 – 9 mq / liter for the smooth supports with medium absorption
Flash point	Component A > 114°C
Preparation of surfaces	New surfaces: New plasters or patches must be well cured, clean, dry and free from white layers. In the presence of mold, treat the surface with suitable restoring products. Remove any efflorescence with brushing or washing. Prime clean surfaces with water – based acrylic fixative products. Already painted surfaces: Remove old paints that are peeling off. Tempera and lime paintings must be completely removed with brushes and washes.
Preparation of the product	Mix the product before the use and add water: Component A 100 Water max 25 - 30 % (first coat) max 10 - 15 % (second coat)
Environmental conditions	Ambient temperature: from + 8 to 40° C Temperature of the support: > 10° C Humidity: 0 - 80 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.
Precautions:	• Do not apply on wet or not well cured supports; • Do not apply at temperature below 10° C; • Do not apply when humidity is above 80 %, in case of imminent rain and in the presence of wind.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening times	10°C 20°C 30°C Dry to touch: 4, 1, 0,5 hours Dry in depth: 8, 4, 2 hours
Time for overpainting	Minimum (hours) 10°C 20°C 30°C 8 4 2 hours Maximum unlimited in the absence of contaminants
Application	Brush, roller If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium - haired rollers. For the application, it is necessary to use the method of crossing coats.
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	L 14 L 5 L 2.5

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it