resina color
made in italy
painting the difference

Scheda Tecnica

CRISTAL





Perfumed water - dilutable paint

Good breathability

It is suitable for internal spaces

Code	0884
Description	Perfumed water - based paint made of copolymers and synthetic pigments that give the product the following characteristics: high coverage, ease of application, excellent elasticity and whiteness. The dry film offers a pleasant satin appearance and it allows a perfect breathability of the surfaces.
Use	It is suitable for any internal walls
Appearance of the film	Matt
Color	White
Component	1
Hardening	Physical hardening through evaporation of water and union of the polymer
Specific weight	From 1,700 gr / ml

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

VOC	30 gr/ liter
Estimated yield	8 - 9 m² / litre for the smooth supports with medium absorption
Flash point	Component A > 114°C
Preparation of surfaces	New surfaces: Make sure that the supports are completely dry. If there are molds, treat the surface with suitable restoring products. Remove any efflorescence and paints that are peeling off with brushes and washes. Prime the surface with a vinyl fixative product diluted in a ratio of 1 litre of insulating product with 8 - 10 litres of water. Old surfaces: Remove old paints that are peeling off. Tempera and lime paintings must be removed with brushes and washes. Prime the surface with a vinyl fixative product diluted in a ratio of 1 litre of insulating product with 8 - 10 litres of water.
Preparation of the product	Mix the product before the use and add water Component A 100 Water 1° coat 20 - 25 % 2° coat 10 - 15 %
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 80 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.

Drying and hardening time	10° C	20° C	30° C	
For the thickness of 50 microns				
Dry to touch	3	1	0,5	hours
Dry in depth	8	4 -5	2	hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Time of overpainting	Minimum (hours) 10° C 20° C 30° C 8 4 3 hours Maximum unlimited in the absence of contaminants
Application	Brush, roller If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium - haired rollers. For the application, it is necessary to use the method of crossing coats.
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Comp A Lt. 14 Lt. 5 Lt. 2,5

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it