Scheda Tecnica

DELICATO





Water - based acrylic finish

Washable

Decorative paint

Code	0711
Description	Precious decorative finish, which has a metallic sheen, based on acrylic resins in water emulsion with an excellent resistance to washing and a high flexibility in application and dilatation, for internal spaces.
Use	It can be applied to wall surfaces, properly prepared with concrete, where a luminescent aesthetic appearance combined with excellent resistance to washing with cleansing agents are required.
Appearance of the film	Metallic
Color	Color chart
Component	1
Hardening	Physical hardening through evaporation of water and union of the polymer
Specific weight	From 1,03 gr/m

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

VOC	40 gr/ liter
Minimum thickness	50 -60 micron
Estimated yield	4-5 m² / kg for a thickness of 50 microns
Flash point	Component A > 114°C
Temperature resistance	Max 60° C
Preparation of surfaces	New surfaces: Apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water). Old surfaces: Remove any parts that are peeling off and, after a careful cleaning of the substrate, apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water).
Preparation of the product	It is ready to use. Mix the product before the use. Component A 100
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 85 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.

Drying and hardening time	For the thickness of 50 microns	10° C	20° C	30° C	
	Dry to touch	3	1	0,5	hours
	Dry in depth	8	4 - 5	2	hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Time of overpainting	Minimum (hours) 10° C 20° C 30° C 8 4 3 hours Maximum unlimited in the absence of contaminants
Application	After an appropriate preparation of the substrate, apply the product as follows: apply a coat of our white primer « SABBIAFOND » with brushes or roller diluted with water to 20 - 25 %. In order to obtain a color of our chart, mix in the amount shown on our chart LINEA PLATINUM of our paste TONER. First coat: apply « DELICATO », not diluted, with a brush. On the surface, the brush strokes must be crossed avoiding painting the same position in the same way. Second coat: after 6 hours, apply a second coat, in the same way, in order to obtain wonderful contrasts of light.
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Comp A Kg. 2 - Kg. 5.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it