Scheda Tecnica

FULL QUARZ





- Paint based on acrylic dispersions
- Excellent coverage
- UV resistant and abrasion

Code	0872
Description	Latex paint formulated with acrylic resins, light resistant pigments and inert quartz.
Use	Inside where abrasion-resistant coatings are required, and outside for the particular resistance to light and weathering. From the application, you can get finish both smooth and orange peel.
Appearance of the film	Matt
Colour	White and color chart
Componenti	1
Hardening	Phisical evaporation and polymer's coalescence
Specific weight	1,560 gr/ml

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

VOC	20 gr/ liter
Theoretical coverage	4 - 5 mq/ litre for smooth finish 2 - 3 mq/litres for orange peel finish
Flash point	> 114°C
Surface preparation	New surfaces New plaster or patches must be cured, clean, dry and not chalking. If mold is present, treat the surface with a suitable healing c treat the surface with a suitable healing cycle. Remove by brushing or washing same efflorescence. Prime clean surfaces with water based acrylic primers, preferably a type solvent. Painted surfaces: Remove the parts paint to flake away: in the presence of lime based paints or tempera, perform the total removal by washing and brushing.
Paint preparation	Mix the paint before use and add water First application max 30% Finish application max 15% To get the orange peel effect: no diluition
Environmental conditions	Room temperature: from + 5 to 40°C Substrate temperature: > di 10°C Humidity: 0 – 80 %
Application	Brush, roller For brush application, use brushes made of nylon or pure bristle. For roller application, use rollers medium hair. For the paint application use the crossed hands method.
Precautions	Do not apply on wet or unseasoned Not apply at temperatures below 10°C Do not apply when humidity exceeds 80%, in case of imminent rain and windy conditions.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening time

	10°C	20°C	30°C
Touch dry after	4	1	0,5
Dry to handle	8	4	2

Time for overcoating

Unlimited in the absence of contaminants

Shelf life

Two years in a cool, dry place (max 40°C)



Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it