


IDROCOLORE



Water - based wall paint

Good washability

It is suitable for internal and external spaces



Prodotti Murali di Preparazione

Code

0811

Description

Based on vinylversatic resins and opaque pigments, « IDROCOLORE » is a washable water - paint indicated for both internal and external applications. It has a good consistency and it is easy to apply.

Use

This product can be applied on wall surfaces, properly prepared with concrete, where a good aesthetic appearance and an excellent resistance to washing with cleansing products are required.

Appearance of the film

Matt

Color

White

Component

1

Hardening

Physical hardening through evaporation of water and union of the polymer

Specific weight	From 1,550 gr/ml											
VOC	40 gr/ liter											
Estimated yield	8 - 9 m² / liter for coat											
Flash point	Component A > 114°C											
Temperature resistance	Max 60°C											
Washability	> 6000 touches											
Preparation of surfaces	New surfaces: Prime with an acrylic insulating product. In the presence of surfaces with high alkalinity (new or lime plasters based on premixed mortar), use a universal neutralizing insulating product, based on alkali resistant resins. The same treatment is recommended for surfaces previously treated with lime or powder materials.											
Preparation of the product	Mix the product before the use and add water <table><tr><td>Component A</td><td>100</td><td></td><td></td></tr><tr><td>Water</td><td colspan="3">1° coat 20 - 25 % / 2° coat 10 - 15 %</td></tr></table>				Component A	100			Water	1° coat 20 - 25 % / 2° coat 10 - 15 %		
Component A	100											
Water	1° coat 20 - 25 % / 2° coat 10 - 15 %											
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 85 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.											
Drying and hardening time	For the thickness of 50 microns	10° C	20° C	30° C								
	Dry to touch	3	1	0,5 hours								
	Dry in depth	8	4 - 5	2 hours								
	Minimum (hours)	10° C	20° C	30° C								

Time of overpainting

	8	4	3 hours
Maximum	unlimited in the absence of contaminants		

Application

Brush, roller
 If you use the brush, you have to use nylon or natural bristle brushes.
 If you use the roller, you have to use medium - haired rollers.
 For the application, it is necessary to use the method of crossing coats.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Lt. 14 Lt. 5 Lt. 2,5

