

Scheda Tecnica

LEGNO VIVO SINTETICO Lucido o Satinato



Use





Glossy finish for wood

Appearance of the film

It is suitable for internal and external spaces

Elastic and resistant to the weather



1102 Code Description Modified long oil synthetic resin for substrate based on wood.

> This product is used for new wood surfaces and on old substrates, previously painted, such as: match - boarding, shutters, fences, attics, and so on.

Glossy and matt flatting

Color Transparent

Component 1

Hardening Physical hardening through evaporation of the solvent and oxidative polymerization

> Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Scheda Tecnica

Specific weight 0,920 gr / ml

Volume of solids 44 %

VOC 400 gr/liter

7 m² / litre for a thickness of 60 microns (2 coats) Estimated yield

34°C Flash point

Preparation of surfaces New or carried forward surfaces:

> Sand in order to remove the raised wood fibers, any traces of resin must be removed with the use of a nitro thinner. Fill any imperfections, sand and remove dust.

Give a first coat of colored filler.

After dying, sand and give a coat of « LEGNO VIVO SINTETICO » for interior applications, two coats for exterior applications.

Already painted surfaces:

Remove old layers of paints that are peeling off and roughen the surface. Sand any fillings and remove dust. Apply the primer as indicated above.

Preparation of the product Mix the product before the use

> Component A 100 0 - 5 % Synthetic thinner

Environmental conditions Ambient temperature: from + 8 to 35° C

Temperature of the support: $> 5^{\circ}$ C Humidity: 0 - 80 % Humidity of the support: < 10 %

10° C Drying and hardening times For the thickness of 60 microns (wet)

20° C 30° C Dry to touch 6 3 1 hours 18 10 Dry in depth 6 hours



Scheda Tecnica

Time of overpainting

Minimum (hours)

10° C 20° C 30° C
18 10 6 hours

Application Brush, roller, spray

If you use the brush, you have to use nylon or natural bristle brushes.

If you use the roller, you have to use medium - haired rollers.

For the application, it is necessary to use the method of crossing coats.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Lt. 4 Lt. 1