Scheda Tecnica

LEGNO VIVO SINTETICO Lucido o Satinato





- Glossy finish for wood
- It is suitable for internal and external spaces
- Elastic and resistant to the weather

Code	1102
Description	Modified long oil synthetic resin for substrate based on wood.
Use	This product is used for new wood surfaces and on old substrates, previously painted, such as: match - boarding, shutters, fences, attics, and so on.
Appearance of the film	Glossy and matt flatting
Color	Transparent
Component	1
Hardening	Physical hardening through evaporation of the solvent and oxidative polymerization

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	0,920 gr / ml
Volume of solids	44 %
VOC	400 gr/ liter
Estimated yield	7 m² / litre for a thickness of 60 microns (2 coats)
Flash point	34°C
Preparation of surfaces	New or carried forward surfaces: Sand in order to remove the raised wood fibers, any traces of resin must be removed with the use of a nitro thinner. Fill any imperfections, sand and remove dust. Give a first coat of colored filler. After dying, sand and give a coat of « LEGNO VIVO SINTETICO » for interior applications, two coats for exterior applications. Already painted surfaces: Remove old layers of paints that are peeling off and roughen the surface. Sand any fillings and remove dust. Apply the primer as indicated above.
Preparation of the product	Mix the product before the use Component A 100 Synthetic thinner 0 - 5 %
Environmental conditions	Ambient temperature: from + 8 to 35° C Temperature of the support: > 5° C Humidity: 0 - 80 % Humidity of the support: < 10 %

Drying and hardening times			
For the thickness of 60 microns (wet)	10° C	20° C	30° C
Dry to touch	6	3	1 hours
Dry in depth	18	10	6 hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Time of overpainting	Minimum (hours)	10° C	20° C	30° C
		18	10	6 hours

Application

Brush, roller, spray
If you use the brush, you have to use nylon or natural bristle brushes.
If you use the roller, you have to use medium - haired rollers.
For the application, it is necessary to use the method of crossing coats.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Lt. 4 Lt. 1

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it