Scheda Tecnica

LUXURY





- Glossy textured finish based on water
- High washability
- It is suitable for internal and external spaces

Code	0905
Description	Paint based on vynilversatic copolymers in aqueous dispersion. It is suitable for the rooms of hospitals, schools, and for all environments where a high standard of cleanliness is required.
Use	This product can be applied to old and new plasters based on hydraulic binders, concrete, plaster and plasterboard surfaces. It is also used on old organic or inorganic paints, provided they are well adherent. Avoid the application on wet or alkaline substrates.
Appearance of the film	Glossy
Color	White and color chart
Component	1
Hardening	Physical hardening through evaporation of water and union of the polymer

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	Da 1,170 gr/m
Volume of solids	43 %
VOC	71,53 gr/ liter
Minimum thickness	100 micron
Estimated yield	4,3 m² / litre for a thickness of 100 microns
Flash point	Component A > 114°C
Preparation of surfaces	New surfaces: Prime with an acrylic insulating product; in the presence of surfaces with high alkalinity (lime plasters), use a universal neutralizing insulating product, based on resistant alkali resins. In the presence of lime or tempera paints, remove them entirely from the surface by washing or by the abrasion. In the presence of mold, provide an adequate anti - mold treatment with suitable products.
Preparation of the product	Mix the product before the use Component A 100 Water max 5 % to reduce the textured effect
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 75 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening time	At 25° C and 65 % of humidity 1 - 2 hours
Time of overpainting	6 hours
Application	Roller, brush only for small touches. For the roller application, use medium - grained sponge rollers.
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Comp A Lt. 14; Lt. 5; Lt. 2,5.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it