Scheda Tecnica

MUROFIX EX





- Water - based primer
- Good penetration
- It is suitable for external places

Code	0638
Description	Water - dilutable stabilizing fixative based on acrylic - styrene copolymers for external use. Since it is pigmented, it gives an initial coverage of the substrate.
Use	This product is suitable for consolidating and making uniform new and old plasters, concrete surfaces, old paints, provided they are dry and well adherent. In addition to improving the characteristics of the plaster, « MUROFIX EX » allows a better application of all wall coverings favoring the perfect anchorage.
Appearance of the film	Matt
Color	White - color chart
Component	1
Hardening	Physical hardening through evaporation of solvents and union of the polymer

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	1,370 gr/ml
Volume of solids	45,5%
VOC	15,3 gr/ litre
Minimum thickness	50 micron
Estimated yield	9,1 m² / litre for a thickness of 50 microns
Flash point	Component A >113°
Preparation of surfaces	Make sure that the substrate is well dry, remove by brushing any efflorescence or all parts of old paints that are peeling off. Completely remove old layers of lime or tempera paint.
Preparation of the product	Mix the product before the use
Thinning	30 - 40% with water
Environmental conditions	Ambient temperature: from + 5 to 35° C Temperature of the support: > 5° C Humidity: 0 - 75 % Avoid application in the presence of surface condensation or under direct sunlight.
Drying and hardening time	At 25° C and 65 % UR 35 - 45 minutes
Time of overpainting	4 – 5 hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Application	Brush, roller If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium - haired rollers. For the application, it is necessary to use the method of crossing coats.
Shelf life	1 year in a cool and dry place (max 40° C)
Packs	Lt. 14 Lt. 5

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it