

Nitrocolor Matte / Glossy



Alkyd nitro enamel

Brilliant and elastic

Brilliant and elastic



Code

0201 - 0202

Description

Modified cellulosic nitro enamel

Use

The product can be used as a finish for industrial vehicles, agricultural machines, industrial equipment. It ensures rapid drying. It has a good resistance to weathering, impacts and abrasion. It can be applied directly on metal sheet. The best results are obtained when the application is done on synthetic surfaces.

Appearance of the film

Brilliant

Colour

White and RAL colours

Componenti

1

Indurimento

Physical by evaporation of the solvents.

Specific weight

1,080 - 1,120

Volume of solids	38%			
Voc	385 gr/lt			
Minimum thickness	50 – 60 micron			
Estimated yield	6,3 m ² / L for a thickness of 60 microns dry.			
Flash point	6°C			
Temperature resistance	Max 100°C			
Preparation of surfaces	Surfaces primed with anti-rust RE or degreased metal sheet			
Preparation of the product	Mix the product before use and add the diluent Component A 100 Thinner Nitro thinner: 20-25 % depending on the thickness of the dry film to be applied.			
Environmental conditions	Ambient temperature: from + 5 to 40°C Temperature of the surface: > 10°C Humidity: 0 – 85 % To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point			
Drying and hardening	For thicknesses of 60 microns	10°C	20°C	30°C
	Dry to touch	1h	25'	12'
	Dry in depth	8h	2h	1h

Time of overpainting

Minimum (hours)	10°C	20°C	30°C
	12	8	6
Maximum	Unlimited, except for the presence of contaminants on the surface		

Application

Spray
Brush for touch ups onl

Shelf life

2 years in a cool and dry place (max 40°C)

Packs

Kg. 20 - Lt. 4 - Lt. 0,750

