Scheda Tecnica

Nitrocolor Matte / Glossy





Alkyd nitro enamel

Brilliant and elastic

Brilliant and elastic

Code	0201 - 0202
Description	Modified cellulosic nitro enamel
Use	The product can be used as a finish for industrial vehicles, agricultural machines, industrial equipment. It ensures rapid drying. It has a good resistance to weathering, impacts and abrasion. It can be applied directly on metal sheet. The best results are obtained when the application is done on synthetic surfaces.
Appearance of the film	Brilliant
Colour	White and RAL colours
Componenti	1
Indurimento	Physical by evaporation of the solvents.
Specific weight	1,080 – 1,120

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Volume of solids	38%
Voc	385 gr/lt
Minimum thickness	50 – 60 micron
Estimated yield	6,3 m² / L for a thickness of 60 microns dry.
Flash point	6°C
Temperature resistance	Max 100°C
Preparation of surfaces	Surfaces primed with anti-rust RE or degreased metal sheet
Preparation of the product	Mix the product before use and add the diluent Component A 100 Thinner Nitro thinner: 20-25 % depending on the thickness of the dry film to be applied.
Environmental conditions	Ambient temperature: from + 5 to 40°C Temperature of the surface: > 10°C Humidity: 0 – 85 % To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point

Drying and hardening			
For thicknesses of 60 microns	10°C	20°C	30°C
Dry to touch	1h	25’	12’
Dry in depth	8h	2h	1h

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Time of overpainting	Minimum (hours) 10°C 20°C 30°C 12 8 6 Maximum Unlimited, except for the presence of contaminants on the surface
Application	Spray Brush for touch ups onl
Shelf life	2 years in a cool and dry place (max 40°C)
Packs	Kg. 20 - Lt. 4 - Lt. 0,750

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it