Scheda Tecnica

NUBILAC SATINATO





- High coverage
- Excellent washability
- Quick drying

Code	0309
Description	Satin enamel based on acrylic resins in aqueous emulsion and precious pigments, which give the product a very high coverage, high yield, exceptional washability, high resistance to chemical and atmospheric agents, and perfect adhesion on various types of support such as PVC, light alloys and old paintwork. Being completely solvent-free, the new NUBILAC is non-toxic, odorless and non-flammable and can also be applied in closed or poorly ventilated environments without any danger as it does not create harmful or disturbing vapors.
Use	The product can be applied on various types of surfaces such as PVC, light alloys, old paints, wood, iron, glass, wall and concrete surfaces, on the condition that they are properly prepared and primed. .
Appearance of the film	satin
Colour	White – Black – Colour chart
Component	1

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Hardening	Physical by evaporation of water and coalescence of the polymer.
Specific weight	From 1,30 gr/lt
Volume of solids	38,8 %
VOC	48 gr/ liter
Minimum thickness	50 -60 micron
Estimated yield	6,4 m² /L for a thickness of 50 microns dry
Flash point	Component A > 114°C
Temperature resistance	Max 60°C
Preparation of surfaces	New surfaces: Prime with acrylic insulation IMPRIMITURA ACRILICA. In case of surfaces with high alkalinity (lime plasters) use the universal neutralizing insulator H95 IMPRIMITURA based on resistant alkali resins. The same treatment is advisable in case of surfaces previously treated with lime or chalking. Metal surfaces: prime with the water-based anti-rust product UNDER.
Preparation of the product	Mix the product before use and add water. Component A 100 Water 10-15% max.
Environmental conditions	Ambient temperature: from + 5 to 40°C Temperature of the surface: > 10°C Humidity: 0 – 85 % To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening

For thicknesses of 50 microns	10°C	20°C	30°C	
Dry to touch	3	1	0,5	hrs
Dry in depth	8	4 -5	2	

Time of overpanting

Minimum (hrs)	10°C	20°C	30°C
	8	4	3

Maximum Unlimited, except for the presence of contaminants on the surface

Application

Brush, roller spray
For brush applications use nylon or pure bristle brushes.
For roller applications use medium pile rollers.
For the application use the method of the crossed hands.

Shelf life

2 years in a cool and dry place (max 40°C)

Packs

Comp A Lt. 2,5 Lt. 0,750

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it