Scheda Tecnica

PERLA

Acrylic water-based putty

Washable

Pearlescent

Code	0714
Description	Putty based on acrylic resins in aqueous emulsion and special pigments that give the product some particular effects typical of gold and silver. PERLA is a washable product
Use	It can be applied on suitably prepared concrete wall surfaces where a pearlescent aesthetic appearance is required combined with excellent resistance to washing with detergents.
Appearance of the film	Pearlescent
Colour	Colour chart
Component	1
Hardening	Physical by evaporation of water and coalescence of the polymer.
Specific weight	From 1,03 gr/m

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

VOC	40 gr/ liter
Minimum thickness	50 -60 micron
Estimated yield	4-5 m² / kg for a thickness of 50 microns dry
Flash point	Component A > 114°C
resistance to temperature	Max 60°C
Preparation of surfaces	New surfaces: Apply one coat of our IMPRIMITURA ACRILICA insulator diluted with water in a ratio of 1 to 5 (for each liter of IMPRIMITURA ACRILICA mix 5 liters of water). Old surfaces: remove all the peeling parts, and after a careful cleaning of the surface, apply a coat of our ACRYLIC IMPRIMITURA diluted with water in a ratio of 1 to 5 (for each liter of ACRYLIC IMPRIMITURA mix 5 liters of water).
Preparation of the product	Ready to use. Mix the product before use. Component A 100
Environmental conditions	Ambient temperature: from + 5 to 40°C Temperature of the surface: > 10°C Humidity: 0 – 85 % To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point

Drying and hardening	10°C	20°C	30°C	
For thicknesses of 50 microns				
Dry to touch	3	1	0,5	hrs
Dry in depth	8	4 -5	2	

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

overpainting	Minimum (hours) 10°C 20°C 30°C 8 4 3 Maximum Unlimited, except for the presence of contaminants on the surface
Application	After adequate preparation of the surface, apply the product as follows: apply a coat of our SABBIAFOND white primer of the same tone as the finish with a brush or roller diluted with 20-25% water. To obtain a colour from our bundle, mix the quantity indicated on our PLATINUM LINE folder.Add and mix our TONER coloring pastes. First coat: spread PERLA evenly undiluted with the appropriate plastic trowel, putting a good amount of product and smoothing until a smooth surface is obtained. Second coat: after 4-5 hours, always apply a second coat with the appropriate plastic trowel, creating crossed spots from right to left from top to bottom, with gentle movements, thus creating the desired decoration.
Shelf life	2 years in a cool and dry place (max 40°C)
Packs	Comp A Kg. 2 – Kg. 5.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it