

PITTURA PER COPERTA



Alkyd non - slip finish

Brilliant and elastic

Excellent resistance to atmospheric agents



Code

1007

Description

Finish based on glycerophthalic resins modified with no yellowing siccative oils which give to the product a high UV resistance, an excellent flexibility in application, the hardness of the surface and a high resistance to atmospheric agents and salts. When the product is completely dry, it provides a non - slip surface.

Use

This product is used as a finish for wooden and iron decks of tourist or work boats such as yachts, fishing boats, « gozzi » (Ligurian fishing boats), tug - boats and ships in general.

Appearance of the film

This product is used as a finish for wooden and iron decks of tourist or work boats such as yachts, fishing boats, « gozzi » (Ligurian fishing boats), tug - boats and ships in general.

Color

White - green - red - light blue

Component

1

Hardening

Physical hardening through evaporation of solvents and oxidative polymerization

Specific weight	1,000 – 1,140 g r/ ml
Volume of solids	51 %
VOC	380 gr/ liter
Minimum thickness	50 – 60 micron
Estimated yield	8.5 m ² / litre for a thickness of 60 microns
Flash point	Component A 34°C Thinner 34°C
Temperature resistance	Max 100° C continuously or 140° C discontinuously
Preparation of surfaces	Iron: make sure that the substrate is well clean, dry and degreased. Remove any rust stains and apply a coat of an anti - rust product such as « RESINFER », « RESINCOR R.E. », « RESINZINC » or « MINIOCROM ». Wood: apply a coat of « MINIOCORM » and two coats of « PITTURA PER COPERTA ».
Preparation of the product	Mix the product before the use and add the thinner Component A 100 Thinner 5 - 10 % according to the thickness of the dry film to be applied

Environmental conditions

Ambient temperature: from + 5 to 40° C
 Temperature of the support: > 10° C
 Humidity: 0 - 85 %
 In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.

Drying and hardening time

For the thickness of 45 microns	10° C	20° C	30° C
Dry to touch	4	2	1 hours
Dry in depth	24	12	6 hours

Time of overpainting

Minimum (hours)	10° C	20° C	30° C
	24	12	6 hours
Maximum	unlimited in the absence of contaminants		

Application

Brush, roller, spray
 If you use the brush, you have to use nylon or natural bristle brushes.
 If you use the roller, you have to use short - haired rollers.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Lt. 16, Lt. 2,5, Lt. 0,750 Thinner Lt. 25 - Lt. 5 - Lt.