Scheda Tecnica

Casapura





- Water-soluble anti-mould paint
- Breathable paint
- Suitable for external use

Code	0803
Description	IBreathable anti-mould hydro paint for walls incorporated with a high concentration of anti-mould and anti-alagae salts. This anti-mould paint has a good coating and spread capacity and an excellent adehesion to the surface.
Use	Casapura is recommended for the painting of inner walls which need protection from mould. It is suggested for places where steam is generated: kitchens, bathrooms, greenhouses, cheese factories, slaughterhouses, swimming pools, breweries.
Appearance of the film	Matt
Color	White and colour chart
Component	1
Hardening	Physical by evaporation of water and coalescence of the polymer.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	From 1,600 gr/ml
VOC	40 gr/ liter
Estimated yield	8 - 9 m²/ L for smooth medium absorption surfaces
Flash point	Component A > 114°C

Preparation of surfaces

New surfaces:
Make sure that the surfaces are completely dry. In case of mould, treat the surface with suitable healings.
Eliminate any efflorescence and detaching paints by brushing and washing them.
Prime with acrylic fixative.
Old paints:
Eliminate the old detaching paints. Paints based on tempera and lime should be removed by brushing and washing.

Preparation of the product

Mix the product before use and add water

Component A	100
Water	max 30%

Environmental conditions

Ambient temperature: from + 5 to 40°C
Temperature of the surface: > 10°C
Humidity: 0 – 80 %
To prevent the formation of condensation, the temperature of the surface must be at least 3 ° C higher than the dew point.

Drying and hardening time

For thicknesses of 50 microns	10°C	20°C	30°C	
Dry to the touch	3	1	0,5	hours
Dry in depth	8	4 -5	2	

Time of overpainting

Minimum: (hrs)	10°C	20°C	30°C
	8	4	3

Maximum: unlimited, except for the presence of contaminants on the surface.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Application	Brush and paint roller. For brush applications use nylon or pure bristle brushes. For roller applications use medium-hair rollers. For the application use the method of the crossed hands
Shelf life	2 years in a cool and dry place (max 40 ° C)
Packs	Comp A L 14 L5 L 2.5



Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it