Scheda Tecnica

PRIMER ANTIMUFFA - ANTIALGHE





- Acrylic primer
- Good penetration
- Mildew, fungi and algae resistent

Code	0613
Description	Impregnating resin based styrene - acrylic fortified with special additives with high power algae and mold.
Use	As support for the anchoring of subsequent layers of paint on new plaster or old, who are infested with molds: rooms with high humidity, north-facing walls. Also suitable for media of various kinds, as long as absorbent or old paints compact and adherent.
Appearance of the film	Translucent
Colour	Trasparent – Yellow – White – Black – Oxide Red
Component	1
Hardening	Phisical evaporation and polymer's coalescence

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	1,01 gr/ml
Volume of solids	26 %
VOC	5 gr/ liter
Minimum thickness	5 – 10 micron
Estimated yield	26 mq / litro on substrates in the medium absorption
Preparation of surfaces	New surfaces Make sure they are completely dry, in the presence of mold, treat the surfaces with suitable restorative. Remove efflorescence by washing and brushing, primed with acrylic mold fixative. Painted surfaces: Remove old paint or flaking; old lime paints must be removed by washing and brushing.
Preparation of the product	Mix the paint before use and add water First application max 50%
Environmental conditions	Room temperature: from + 5 to 40°C Substrate temperature: > di 10°C Humidity: 0 – 80 %

curing time

For thickness 50 microns	10°C	20°C	30°C
Touch dry after	1,5	1	0,5(hours)
Dry to handle	3	2	1

Time for Overpainting	4 – 5 hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Application	Brush, roller For brush application, use brushes made of nylon or pure bristle. For roller application, use rollers medium hair. For the paint application use the crossed hands method.
Shelf life	Two years in a cold dry place (max 40°C)
Packs	Comp A Lt. 20 Lt. 5 Lt. 1

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it