resina color
made in italy
painting the difference

Scheda Tecnica

QUARZO BUCCIA D'ARANCIA

Thick coating

Permeable to water vapour

Resistant to the bad weather

Code	0906
Description	Based on water dispersion copolymers, opaque pigments and selected quartzes, the product is a quartz plastic coating with an orange peel final effect with remarkable characteristics of resistance to the impacts, abrasions and washings.
Use	This product can be applied on old and new plasters based on hydraulic binders, on concrete, on old organic and mineral paints, provided they are absorbent and united.
Appearance of the film	Matt
Color	White or color chart
Component	1
Hardening	Physical hardening through evaporation of water and union of the polymer
Specific weight	From 1,670 gr/ml

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

VOC	15 gr/ liter
Estimated yield	1 - 1,5 kg / m²
Flash point	Component A > 114°C
Preparation of surfaces	New surfaces: Dry and mature. Remove any efflorescence by brushing or washing. Old surfaces: Remove dust and all old paints that are peeling off, widen any cracks and fill them with a filler. Completely eliminate old lime or tempera paints. In the presence of molds, provide for an appropriate anti - mold treatment. Prime surfaces with an acrylic fixative such as « IMPRIMITURA ACRILICA » or « SOTTOFONDO ».
Preparation of the product	Mix the product before the use. Component A 100 Thinner Water Brush 1° coat dilute to 25 - 30 %; 2° coat to 10 - 15 % Roller: 10 - 15 % max.
Environmental conditions	Ambient temperature: from + 8 to 40° C Temperature of the support: > 5° C Humidity: 0 - 75 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.
Precautions:	Do not apply in the presence of surface condensation or under direct sunlight. The humidity of the substrate must be less than 10 %. Protect from the rain for at least 48 hours.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening time	At 25° C for 0,5 - 1 hour depending on the thickness applied
Time for overpainting	After 4 – 5 hours
Application	« QUARZO BUCCIA D'ARANCIA » is applied with a brush or a wool roller. In addition, it is worked with an orange peel roller and it is diluted with max 3 - 4 % of water; so we obtain the classic orange peel effect.
Shelf life	1 year in a cool and dry place (max 40° C)
Packs	Comp A Lt. 14, Lt. 4, Lt. 2,5

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it