Scheda Tecnica

QUARZO LUX EXTRA





- Made of quartz flour
- Excellent washability
- Resistant to the bad weather

Code	0818
Description	Finish made of acrylic resins in emulsion, photo – resistant pigments. This product has an excellent washability and a good ease in application. It lets the wall breathe, offering an excellent resistance to the bad weather..
use	« QUARZO LUX EXTRA » is used for the painting of the exterior and interior walls, constructions in reinforced concrete, gypsum, exposed bricks, and so on. In addition to exalting the resistance features, quartz allows to apply thicknesses that are superior to the normal washable paints. So it masks any imperfections of the support.
Appearance of the film	Matt
Colour	White – color chart
Component	1
Hardening	Evaporation of the solvents and union of the polymer

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	From 1,527 gr/lt
Volume of solids	43 %
VOC	9,2 gr/ liter
Minimum thickness	50 -60 micron
Estimated yield	8,6 m² / litre for a thickness of 50 micron
Flash point	Component A > 114°C
Resistance to the temperature	Max 60° C
Preparation of surfaces	New surfaces: Prime with an acrylic insulating product (« Imprimitura Acrilica »). If there are surfaces with high alkalinity (lime plasters, new ready – mix plasters), use a neutralizing universal insulating product, based on resistant alkali resins (« Primer/P »). It is recommended to do the same operation if there are surfaces previously treated with lime or flour.
Preparation of the product	Mix the product before the use and add water Component A 100 Water max 40 %

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Environmental conditions	Ambient temperature: from + 8 to 40° C Temperature of the support: > 10° C Humidity: 0 – 80 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.
Drying and hardening time	For the thickness of 50 micron 10°C: 3 hours Dry to touch, 8 hours in depth 20°C: 1 hours Dry to touch, 4-5 hours in depth 30°C: 0,5 hours Dry to touch, 2 hours in depth
Time of overpainting	Minimum 10°C - 8 hours 20°C - 4 hours 30°C - 3 hours Maximum unlimited in the absence of contaminants
Application	Brush, roller, spray If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium-haired rollers. For the application, it is necessary to use the method of crossing coats.
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Comp A Lt. 14 Lt. 5 Lt. 2,5

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it