

Scheda Tecnica

RESINFER









Anti - corrosion primer

Excellent adhesion of iron and steel alloys

Fast in drying



0505 Code Description Anti - corrosion primer based on modified glycerophthalic resins, with good anti corrosive properties with barrier effect. Use This product is used as a primer coat on new or already painted iron or steel alloys, exposed in low and medium aggressive environments. It must always be coated with a synthetic finishing coat. Matt Appearance of the film Color Grey 1 Component Hardening Physical hardening through evaporation of solvents and oxidative polymerization.

Specific weight 1,500 gr/ml

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Scheda Tecnica

Volume of solids 51 %

VOC 380 gr/ liter

Minimum thickness 50 - 60 micron

Estimated yield 8,5 m² / litre for a thickness of 60 micronsi

Flash point Component A 34°C Thinner 34°C

Temperature resistance 90° C continuously, 120 °C discontinuously.

Preparation of surfaces New steel:

SA 2 sandblasting or mechanical brushing, anyway clean surfaces. If the surfaces are new and free of calamine, a washing with solvent is sufficient.

Old paints:

Remove all old paints that are peeling off by scraping or mechanical brushing. For those parts well adherent, a sanding followed by a dust removal is sufficient.

Preparation of the product Mix the product before the use and add the thinner

Component A 100

Thinner 5 - 10 % synthetic thinner

Environmental conditions Ambient temperature: from + 5 to 35° C

Temperature of the support: $> 10^{\circ}$ C Humidity: $0 - 80^{\circ}$

In order to prevent the formation of condensation, it is necessary that the

temperature of the substrate is at least 3° C above the dew point.



Scheda Tecnica

Daniel and	1	la a sal a sa	the security of
Drvina	and	narden	ina time

For the thickness of 60 microns	10° C	20° C	30° C
Dry to touch	6	2	1 hours
Dry in depth	12	8	6 hours

Time of overpainting

Minimum (hours)	10° C	20° C	30° C	
	12	8	6 hours	
Maximum unlimited in the abse	ence of contami	inants		

Application

Brush, roller, spray

If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium - haired rollers. For the application, it is necessary to use the method of crossing coats.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A: Lt. 16 - Lt. 2,5 - Lt. 0,500 Thinner: Lt. 25 - Lt. 5 - Lt. 1 - Lt. 0,500