Scheda Tecnica

RESINFILL DUO





- Spatula synthetic putty
- Easy application
- Good adhesion and resistance

Code	0407
Description	Single-component paste synthetic putty, based on alkyd and urethane resins, for wood and metal. Exceptional adhesion and surface hardness. Easy to sand both dry and wet.
Use	Suitable for application at low and medium thickness to achieve uniform surfaces. Used for the preparation of large and small surfaces, in wood and metal (properly treated).
Appearance of the film	Matt
Color	White
Components	1
Viscosity	Pasty
Elasticity	Good

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Adhesion	Excellent
Hardness	Excellent
Hardening	Physical solvent evaporation
Specific weight	1.900 gr/ml
Dry residue	80%
VOC	342 gr/ litro
Estimated yield	Variable depending on thickness
Flash point	Component A > 23°C
Preparation of surfaces	Remove any traces of oil or rust, friable parts, or areas in the process of detaching through mechanical cleaning or sanding. If necessary, apply a coat of universal primer EPOFOND ZINC or CEMNTIK depending on the substrate.
Preparation of the product	Ready to use
Environmental conditions	Room temperature: from + 10 to 35°C Surface temperature: > di 10°C Humidity: 0 – 85 % To prevent the formation of condensation is necessary that the temperature of the substrate is at least 3 ° C above the dew point.

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Drying and hardening time	Dry to the touch 2 hours Through drying 24 hours
Application	Spatula
Shelf life	2 years in a cool, dry place (max 40 ° C)
Packs	Lt. 0,500



Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it