

Scheda Tecnica

RESINFILL DUO





Spatula synthetic putty

Easy application

Good adhesion and resistance



Code 0407 Description Single-component paste synthetic putty, based on alkyd and urethane resins, for wood and metal. Exceptional adhesion and surface hardness. Easy to sand both dry and wet. Use Suitable for application at low and medium thickness to achieve uniform surfaces. Used for the preparation of large and small surfaces, in wood and metal (properly treated). Appearance of the film Matt Color White Components Viscosity **Pasty** Elasticity Good

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Scheda Tecnica

| Adhesion | Excellent |
|----------------------------|--|
| | |
| Hardness | Excellent |
| | |
| Hardening | Physical solvent evaporation |
| ı | |
| Specific weight | 1.900 gr/ml |
| | |
| Dry residue | 80% |
| | |
| VOC | 342 gr/ litro |
| | |
| Estimated yield | Variable depending on thickness |
| | |
| Flash point | Component A > 23°C |
| | |
| Preparation of surfaces | Remove any traces of oil or rust, friable parts, or areas in the process of detaching through mechanical cleaning or sanding. If necessary, apply a coat of universal primer EPOFOND ZINC or CEMNTIK depending on the substrate. |
| | |
| Preparation of the product | Ready to use |
| | |
| Environmental conditions | Room temperature: from $+$ 10 to 35°C Surface temperature: $>$ di 10°C Humidity: 0 - 85 % To prevent the formation of condensation is necessary that the temperature of the substrate is at least 3 ° C above the dew point. |
| | |



Scheda Tecnica

Through drying 24 hours

Application Spatula

Shelf life 2 years in a cool, dry place (max 40 ° C)

Packs Lt. 0,500

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it