Scheda Tecnica

Resing





- Modified alkyd finish
- Brilliant and elastic
- Excellent resistance to the atmospheric agents

Code	0101
Description	Finish based on urethane - alkyd resins
Use	This product is used as a final coat in synthetic cycles for the protection of wood products and manufactures to be used in industrial and marine environments.
Appearance of the film	Brillant
Color	White - color chart - RAL colors
Component	1
Hardening	Physical hardening through evaporation of solvents and oxidative polymerization

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Specific weight	1,000 - 1,180
Volume of solids	50 - 55%
Voc	380 gr/ liter
Minimum thickness	50 - 60 micron
Estimated yield	10 m² / liter for a thickness of 50 microns
Flash point	>34°C
Brillance	> 90 Gloss
Temperature resistance	100° C continuously 140° C discontinuously
Preparation of surfaces	Surfaces primed with a synthetic or epoxy prime
Preparation of the product	Mix the product before the use and add the thinner Component A 100 Thinner 5 - 10 % depending on the thickness of the dry film to be applied.
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 85 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.
Drying and hardening time	For the thickness of 80 microns (wet) 10° C 20° C 30° C Dry to touch 6 2 1 hours Dry in depth 24 12 8 hours
	Minimum (hours) 10° C 20° C 30° C

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Time of overpainting	24 12 8 hours
Maximum (months)	unlimited after the removal of contaminants
Application	Brush, roller, spray If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium - haired rollers. For the application, it is necessary to use the method of crossing coats.
Shelf life	1 year in a cool and dry place (max 40° C)
Packs	Lt. 2,5; Lt. 0,750

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it