

# SABLE



Acrylic finish based on water

Washable

Luminescent



Code

0710

Description

Washable finish for internal rooms based on acrylic resins in water emulsion and special luminescent particle - size pigments, which gives the product a special reflection of sand.

Use

This product can be applied to wall surfaces, properly prepared with concrete, where a luminescent aesthetic appearance combined with excellent resistance to washing with cleansing agents are required.

Appearance of the film

Luminescent

Color

Color chart

Component

1

Hardening

Physical hardening through evaporation of water and union of the polymer

Specific weight	From 1,41 gr/lt
VOC	40 gr/ liter
Minimum thickness	50 -60 micron
Estimated yield	9 m <sup>2</sup> / kg for a thickness of 50 microns
Flash point	Component A > 114°C
Temperature Resistance	Max 60°C
Preparation of surfaces	<p>New surfaces: Apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water).</p> <p>Old surfaces: remove any parts that are peeling off and, after a careful cleaning of the substrate, apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water).</p>
Preparation of the product	<p>Product ready to use. Mix the product before the use</p> <p>Component A 100</p>
Environmental conditions	<p>Ambient temperature: from + 5 to 40° C</p> <p>Temperature of the support: &gt; 10° C</p> <p>Humidity: 0 - 85 %</p> <p>In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.</p>

### Drying and hardening time

For the thickness of 50 microns	10° C	20° C	30° C
Dry to touch	3	1	0,5 hours
Dry in depth	8	4 - 5	2 hours

### Time of overpainting

Minimum (hours)	10° C	20° C	30° C
	8	4	3 hours
Maximum	unlimited in the absence of contaminants		

### Application

After an appropriate preparation of the substrate, apply the product as follows:  
 Apply a coat of our white primer « SABBIAFOND » with a brush or a roller diluted with water to 20 - 25 %. In order to have the colors of our color chart, add the amount shown on the chart « Platinum Line » of our dye Toner.  
 Apply a coat of « SABLE », undiluted, with the special brush.  
 You can have two effects depending on the application method:  
 Puff effect: the product is applied with the special brush, always following the same direction.  
 Storm effect: the product is applied crossing brush strokes in an irregular way, paying particular attention to not leave areas where the paint is spread precisely.  
 Wait a few minutes and pass again the special brush without color on the surface

### Shelf life

2 years in a cool and dry place (max 40° C

### Packs

Comp A Kg. 2 - Kg. 5.