

TENNIS



Excellent adhesion on cement and old paints

Good resistance to alkaline and acid solutions

Excellent UV resistance



Code

1001

Description

Solvent-based modified chlorine vinyl resin based paint with good penetrating power

Use

For the protection of concrete tennis courts

Appearance of the film

matt

Colour

Red

Component

1

Hardening

Physical by evaporation if solvents

Specific weight

1,350 gr/ml

Volume of solids	38 %							
VOC	600 gr/ liter							
Estimated yield	5 -6 m² / L per layer and on smooth and medium absorption surfaces							
Flash point	Component A	34°C						
	Thinner	34°C						
Preparation of surfaces	New surfaces: Make sure that the surface is free from humidity, remove any efflorescence by brushing. Old surfaces: Remove any peeling parts, level out any irregularities, seal any cracks. Old paints: Remove by brushing peeling paints and other contaminants. In case of mould, do a preventive wash with a suitable restorer before brushing.							
Preparation of the product	Mix the product before use and add the thinner <table><tr><td>Component A</td><td>100</td></tr><tr><td>Thinner</td><td>max 10% - 15% synthetic thinner</td></tr></table>				Component A	100	Thinner	max 10% - 15% synthetic thinner
Component A	100							
Thinner	max 10% - 15% synthetic thinner							
Environmental conditions	Ambient temperature: from+ 5 to 40°C Temperature of the surface: >10°C Humidity: 0 – 80 % Humidity of the surface < 10% To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point							
Drying and hardening times		10°C	20°C	30°C				
	Dry to touch	6	3	2 hours				
	Dry in depth	12	6	4				

Time for overpainting

Minimum (hours)	10°C	20°C	30°C
	12	6	4
Maximum Unlimited, except for the presence of contaminants on the surface			

Application

Brush, roller, spray

For brush applications use nylon or pure bristle brushes.
For roller applications use medium pile rollers.
For the application use the method of the crossed hands

Shelf life

2 years in a cool and dry place (max 40°C)

Packs

Comp A kg Thinner 5, 25, 180 lt