Scheda Tecnica

TENNIS





- Excellent adhesion on cement and old paints
- Good resistance to alkaline and acid solutions
- Excellent UV resistance

Code	1001
Description	Solvent-based modified chlorine vinyl resin based paint with good penetrating power
Use	For the protection of concrete tennis courts
Appearance of the film	matt
Colour	Red
Component	1
Hardening	Physical by evaporation if solvents
Specific weight	1,350 gr/ml

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Volume of solids	38 %
VOC	600 gr/ liter
Estimated yield	5 -6 m² / L per layer and on smooth and medium absorption surfaces
Flash point	Component A 34°C Thinner 34°C
Preparation of surfaces	New surfaces: Make sure that the surface is free from humidity, remove any efflorescence by brushing. Old surfaces: Remove any peeling parts, level out any irregularities, seal any cracks. Old paints: Remove by brushing peeling paints and other contaminants. In case of mould, do a preventive wash with a suitable restorer before brushing.
Preparation of the product	Mix the product before use and add the thinner Component A 100 Thinner max 10% - 15% synthetic thinner
Environmental conditions	Ambient temperature: from+ 5 to 40°C Temperature of the surface: >10°C Humidity: 0 – 80 % Humidity of the surface < 10% To prevent the formation of condensation the temperature of the surface must be at least 3°C higher than the dew point
Drying and hardening times	10°C 20°C 30°C Dry to touch 6 3 2 hours Dry in depth 12 6 4

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Time for overpainting	Minimum (hours) 10°C 20°C 30°C 12 6 4 Maximum Unlimited, except for the presence of contaminants on the surface
Application	Brush, roller, spray For brush applications use nylon or pure bristle brushes. For roller applications use medium pile rollers. For the application use the method of the crossed hands
Shelf life	2 years in a cool and dry place (max 40°C)
Packs	Comp A kg Thinner 5, 25, 180 lt

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it