resina color
made in italy
painting the difference

Scheda Tecnica

Toplac

Alkyd finish

Matt

Excellent resistance to the atmospherical agents

Code	0102 - 0103
Description	Finish based on modified glycerophthalic resins with non - yellowing siccative oils. a.
Use	This product is used as a finish for metal structures exposed in rural and marine environments.
Appearance of the film	polished / frosted
Color	White and color chart
Component	1
Hardening	Physical hardening through evaporation of solvents and oxidative polymerization
Specific weight	1,000 – 1,180

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Volume of solids	51%
Voc	380 gr/liter
Minimum thickness	50 – 60 micron
Estimated yield	8,5 m² / litre for a thickness of 60 microns
Flash point	>34°C
Temperature resistance	Max 100° C continuously, 140° C discontinuously
Preparation of surfaces	Surfaces primed with anti - rust products such as “RESINFER”, “RESINCOR R.E.”, “RESINZINC”.
Preparation of the product	Mix the product before the use and add the thinner Component A 100 Thinner 5 - 10 % depending on the thickness of the dry film to be applied
Environmental conditions	Ambient temperature: from + 5 to 40° C Temperature of the support: > 10° C Humidity: 0 - 85 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.
Drying and hardening time	For the thickness of 45 microns 10° C 20° C 30° C Dry to touch 4 2 1 hours Dry in depth 24 12 6 hours
Time of overpainting	Minimum (hours) 10° C 20° C 30° C 24 12 6 hours Maximum unlimited in the absence of contaminants

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Application	Brush, roller, spray. If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use short - haired rollers.
Shelf life	2 years in a cool and dry place (max 40° C)
Packs	Lt. 2,5; Lt. 0,750; Lt. 0,375

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it