Scheda Tecnica

VELAX SATINATO





Painting - waterborne semi-gloss enamel

Excellent coverage

Complete washability

Description	Emulsion paint based on acrylic resin dispersed in water .
Use	Indicated for the treatment of surfaces in schools, hospitals , kindergartens, or for environments where we need to ensure a high resistance to washing and sanitizing . Applicable on new plaster or old concrete surfaces , plaster , plasterboard, old paints or absorbent mineral substrates .
Aspect of the film	Semitransparent
Colour	White and folder
Components	1
Physical aspect	water evaporation and coalescence of the polymer.
Specific weight	Da 1,330 gr/ml

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Volume of solids	40%
VOC	12 gr/liter
Estimated yield	6 mq/liter
Flash point	Component A > 114°C
Temperature Resistance	Max 60°C
washability	> 25000 touches
Surface Preparation:	New surfaces: New plaster or patches must be cured, clean, dry and flaky . If mold is present , treat the surface with a suitable healing . Remove efflorescence by brushing or washing . Prime surfaces clean with water-based acrylic fixatives , it is advisable for the exterior solvent-based fixative . Painted surfaces : Remove any parts of paint flaking , in the case of paints distemper or lime predict the total removal by washing and brushing.
Product Preparation:	Mix the product before use and add water Component A 100 Water max 5-10 %
Environmental conditions	Ambient temperature: + 8 to 40 ° C Substrate temperature : > 10 ° C Humidity : 0-80 % To prevent the formation of condensation is necessary that the temperature of the substrate is at least 3 ° C above the dew point .
Precautions:	Do not apply on wet or uncured Do not apply at temperatures below 10 ° C Do not apply when humidity exceeds 80 % , in case of rain and windy conditions.
Drying and curing thickness	from 100 microns 10 ° C 20 ° C 30 ° C Touch dry after 3 1 .5 hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

	Cured 8 4 2
Minimum time for overcoating:	(hours) 10 ° C 20 ° C 30 ° C 8 4 2 Unlimited maximum in the absence of contaminants
Application	Brush , roller or spray For brush application use brushes in nylon or bristle . For roller applications use a medium-haired roller . For the application to use the method of crossed hands
Shelf life	2 years in a cool dry place (max 40 ° C)
Packs	Lt. 14 - Lt. 5 - Lt. 2,5

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it