Scheda Tecnica

VERNICE PER CEMENTO FACCIA VISTA A SOLVENTE





- Resistent to atmospheric agents
- Resistant to the abrasion
- Water - repellent

Code	0830
Description	« VERNICE PER CEMENTO F.V. SOLVENTE » is a product based on acrylic - styrene resins with silicone modification, which makes the substrate water - repellent and highly resistant to the chemical and atmospheric agents.
Use	This product is used as a transparent finish where a good chemical resistance and a resistance to the abrasion are required. It can be used as an anti - dust for concrete.
Appearance of the film	glossy
Color	Opalescent transparent
Component	1
Hardening	Physical hardening through evaporation of water
Specific weight	0,930 gr/ml

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Volume of solids	27 %
VOC	620 gr/ liter
Minimum thickness	60 -80 micron
Estimated yield	4,5 m² / litre for a thickness of 60 mcirons
Flash point	Component A 34° C Thinner 34° C
Temperature resistance	Max 110° C continuously, 200° C discontinuously
Preparation of surfaces	New metal substrates: Remove from the surface dust and contaminants such as grease and oils. For new wood: Give a first diluted coat, remove fiber raising woods by abrasion and give a second coat. For new plaster Appropriate dust removal: application of a diluted coat followed, after 24 hours, by another coat as it is or slightly diluted.
Preparation of the product	Mix the product before the use and add the thinner. Component A 100 Thinner: water 60 % - 80 % (First coat) 10 % - 20 % (Second coat)

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Environmental conditions

Ambient temperature: from + 5 to 40° C
Temperature of the support: > 10° C
Humidity: 0 - 85 %
In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.

Drying and hardening time

For the thickness of 20 microns	10° C	20° C	30° C
Dry to touch	6	3	2 hours
Dry in depth	48	24	10 hours

Time of overpainting

Minimum (hours)	10° C	20° C	30° C
	24	12	6 hours

Maximum unlimited in the absence of contaminants

Application

Brush, roller, spray
If you use the brush, you have to use nylon or natural bristle brushes.
If you use the roller, you have to use medium - haired rollers.
For the application, it is necessary to use the method of crossing coats.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Lt. 25 Lt. 5 Lt. 1

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it