Scheda Tecnica

VERO LEGNO SINTETICO





- Filler for wood
- Excellent penetration
- Resistant to the atmospherical agents

Code	1101
Description	Transparent primer based on modified glycerophthalic resin
Use	« VERO LEGNO SINTETICO INCOLORE » is suitable for new, old, painted wood. It has a good penetration and it remains unchanged despite the structural changes in wood structure. The product ensures a good protection of the wood against UV rays and all agents that can cause wood degradation.
Appearance of the film	glossy
Color	Colorless and wood chart
Component	1
Hardening	Physical hardening through evaporation of the solvent and oxidative polymerization
Specific weight	0,850 gr / ml

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Volume of solids	23 %
VOC	850 gr/ liter
Estimated yield	6 - 7 m² / litre for woods with medium absorption
Flash point	34°C
Preparation of surfaces	New or carried forward surfaces: Sand in order to remove the raised wood fibers, any traces of resin must be removed with the use of a nitro thinner. Fill any imperfections, sand and remove dust. Give a first coat of filler diluted to 20 %. After dying, sand and give a second coat of « VERO LEGNO SINTETICO INCOLORE » for interior applications, three coats for exterior applications. Already painted surfaces: Remove old layers of paints that are peeling off and roughen the surface. Sand any fillings and remove dust. Apply the primer as indicated above.
Preparation of the product	Mix the product before the use and add water Component A 100 Synthetic thinner 10 - 20 % first coat Second coat as it is

Drying and hardening time

	10° C	20° C	30° C
Dry to touch	6	3	1 hours
Dry in depth	18	10	6 hours

Time of overpainting

Minimum (hours)	10° C	20° C	30° C
	18	10	6 hours

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it

Application	Brush, roller, spray If you use the brush, you have to use nylon or natural bristle brushes. If you use the roller, you have to use medium - haired rollers. For the application, it is necessary to use the method of crossing coats.
Shelf life	2 years in a cool and dry place (max 40° C))
Packs	Comp A: Lt. 4 Lt. 1

Copyright 2026 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy
tel. 0804912873 - email: info@resinacolor.it p.i. 09040010721
www.resinacolor.com - www.resinacolor.it