

Scheda Tecnica

VITRUM LUCIDO









Water - based glossy finish

Odourless, inflammable

Elastic and resistant to the weather



Description

Based on acrylic resins, it is a transparent varnish with a glossy final effect, air drying, quick hardening; the dry film has high resistance to abrasion, atmospheric and chemical agents, good flexibility and compactness.

Use

This product is used on new surfaces and on old substrates, previously painted, both in external and internal places

Appearance of the film Glossy

Color Colorless

Components 1

Hardening Evaporation and union of the polymer

Specific weight 1,000 - 1,050 gr / ml

Volume of solids 33 %

Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Scheda Tecnica

VOC 40 gr/ litre

Estimated yield 8 - 9 m² / litre for wood with medium absorption

Flash point ND

Preparation of surfaces New or carried forward surfaces:

New metal substrates:

Remove dust and contaminants such as grease and oil from the surface.

For new wood:

Apply a thinned first coat, remove the wood hair by abrasion and apply a second

coat.

For new concrete:

Adequate dust removal: apply a thinned coat followed after 24 hours by another

coat as is or slightly thinned.

Preparation of the product Mix the product before the use and add water

Component A 100

Thinner Water 10 - 20 % first coat

5 - 6 % second coat

Environmental conditions Ambient temperature: from + 8 to 35° C

Temperature of the substrate: > 5° C

Humidity: 0 - 75 %

Drying and hardening time

At 25° C and 65 % UR

Dry to touch 1 hour; overpainted after 7 hours



Scheda Tecnica

Application Brush, roller, spray

If you use the brush, you have to use nylon or natural bristle brushes.

If you use the roller, you have to use medium - haired rollers.

For the application, it is necessary to use the method of crossing coats.

Shelf life 2 years in a cool and dry place (max 40° C)

Packs Comp A Lt. 2,5 - Lt. 0,750

