

# CEMENCOLOR



Unsaponifiable and resistant to the weather

It is suitable for any supports

It is resistant to the abrasion



Prodotti Professionali

## Code

0817

## Description

Solvent - based paint made of modified vinyl acrylic resins, with high resistance to the atmospheric agents, alkali and with a good permeability to water vapour.

## Use

This product is applied on different substrates such as: plaster, lime plaster, bituminous surfaces, fibre cement.

## Appearance of the film

Semi - glossy

## Color

White, red and color chart

## Component

1

## Hardening

Physical hardening through evaporation of solvents

## Specific weight

1,3 - 1,4 gr/ml

Volume of solids	45 %			
VOC	480 gr/ liter			
Minimum thickness	7,5 m² / litre for a thickness of 60 microns			
Flash point	Component A	34°C		
	Thinner	34°C		
Temperature resistance	Max 110° C continuously 200° C discontinuously			
Preparation of surfaces	New metal substrates: Remove dust and contaminants, such as greases and oils, from the surfaces. For new concrete Adequate dust removal: application of a diluted coat, followed after 24 hours by an other coat as it is.			
Preparation of the product	Mix the product before the use and add the thinner Component A 100 Thinner max 20 % - 30 % (First coat)			
Environmental conditions	Ambient temperature: from + 8 to 40° C Temperature of the support: > 10° C Humidity: 0 - 85 % In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.			
Tempi di essiccazione e indurimento	For the thickness of 60 microns	10° C	20° C	30° C
	Dry to touch	6	3	2 hours
	Dry in depth	48	24	10 hours
Time of overpainting	Minimum (hours)	10° C	20° C	30° C
		24	12	6 hours

**Application**

Brush, roller, spray  
If you use the brush, you have to use nylon or natural bristle brushes.  
If you use the roller, you have to use medium - haired rollers.  
For the application, it is necessary to use the method of crossing coats

**Shelf life**

2 years in a cool and dry place (max 40° C)

**Packs**

Comp A Lt. 16; Lt. 5    Thinner 5, 25, 180 lt

