

Scheda Tecnica

DELICATO





Water - based acrylic finish

Washable

Use

Decorative paint

Appearance of the film



0711 Code

Description

Metallic

Precious decorative finish, which has a metallic sheen, based on acrylic resins in water emulsion with an excellent resistance to washing and a high flexibility in application and dilatation, for internal spaces.

It can be applied to wall surfaces, properly prepared with concrete, where a luminescent aesthetic appearance combined with excellent resistance to washing with cleansing agents are required.

Color Color chart

Component

Physical hardening through evaporation of water and union of the polymer Hardening

Specific weight From 1,03 gr/m

> Copyright 2018 Resina Color - z.i. Via Mastricale 3 - 70017 Putignano (BA) - Italy tel. 0804912873 - email: info@resinacolor.it p.i. 00379520729 www.resinacolor.com - www.resinacolor.it



Scheda Tecnica

VOC 40 gr/ liter

Minimum thickness 50 -60 micron

Estimated yield 4-5 m² / kg for a thickness of 50 microns

Flash point Component A > 114°C

Temperature resistance Max 60° C

Preparation of surfaces New surfaces:

Apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water). Old surfaces:

Remove any parts that are peeling off and, after a careful cleaning of the substrate, apply a coat of our insulating product « IMPRIMITURA ACRILICA » diluted with water in ratio 1 to 5 (mix each liter of « IMPRIMITURA ACRILICA » with 5 liters of water).

Preparation of the product
It is ready to use. Mix the product before the use.

Component A 100

Environmental conditions Ambient temperature: from + 5 to 40° C

Temperature of the support: $> 10^{\circ}$ C Humidity: 0 - 85%

In order to prevent the formation of condensation, it is necessary that the temperature of the substrate is at least 3° C above the dew point.

Drying and hardening time For the thickness of 50 microns 10° C 20° C 30° C

Dry to touch 3 1 0,5 hours
Dry in depth 8 4-5 2 hours



Scheda Tecnica

Time of overpainting

Minimum (hours) 10° C 20° C 30° C

8 4 3 hours

Maximum unlimited in the absence of contaminants

Application

After an appropriate preparation of the substrate, apply the product as follows: apply a coat of our white primer « SABBIAFOND » with brushes or roller diluted with water to 20 - 25 %. In order to obtain a color of our chart, mix in the amount shown on our chart LINEA PLATINUM of our paste TONER.

First coat: apply « DELICATO », not diluted, with a brush. On the surface, the brush strokes must be crossed avoiding painting the same position in the same way. Second coat: after 6 hours, apply a second coat, in the same way, in order to obtain wonderful contrasts of light.

Shelf life

2 years in a cool and dry place (max 40° C)

Packs

Comp A Kg. 2 - Kg. 5.